


Optically Clear Adhesive Tape

-Acid free
-UV cut

EA184DD

1. Structure of Product




2. Characteristics

ITEM		Unit	EA184DD	Test Method	
Thickness	Heavy Release Film	μm	50	JIS Z0237	
	Adhesive		100		
	Light Release Film		50		
Adhesion	Peel Adhesion (Substrate: Glass)	23°C X 30min	36	JIS Z0237	
		23°C X 24hrs	33		
	Light Release Peel Force	N/50mm	0.08		
	Heavy Release Peel Force		0.52		
Optical (Glass+ OCA)	Trans.%		%	92.2	JIS K7361-1
	Haze		%	0.7	JIS K7136
	L*a*b*	L*	—	96.80	JIS Z8729
		a*	—	-0.34	
		b*	—	0.76	

< Technical Data > The test data is measurements and not a guaranteed value.

3. Total Luminous Transmittance Spectrum



Wavelength(nm)	340	360	380
Transmittance(%)	0.0	0.0	0.3

< Technical Data > The test data is measurements and not a guaranteed value

K0534111201Y